



LIVALLCO STÅL AB
SMITH & STENSSON

Bearing steel
102Cr6

DESIGNATIONS

Swedish standard	
ASTM / ASME standard	
Similar grade	
W.stoff nr	1.2067

CHEMICAL COMPOSITION

C	0,95 - 1,10
Cr	1,35 - 1,60
Mn	0,20 - 0,40
Mo	max. 0,10
Ni	max. 0,40
P	max. 0,025
S	max. 0,025
Si	0,15 - 0,35
Fe	rest.

DIMENSION

Plate	Yes
Roundbar	Ø 20 - 450 mm
Flat/Square	
Hexagon	
Forging	Yes
Pipe	

MECHANICAL PROPERTIES

Yield
Tensile
KV

For more information, please contact LIVALLCO STÅL AB, Sweden
Tel. +46 (0)302-150 10 info@livallco.se