



LIVALCO STÅL AB
SMITH & STENSSON

Alloyed **BOILER AND PRESSURE VESSELS STEEL**
acc. to EN 10028

Euronorm

Sw Std

ASTM

W.St.

Pipes

13CrMo4-5
(13CrMo44)

SS 2216

A 387 gr. 12

1.7335

A 335 P12

C	Si	Mn	P	S	Cr	Mo	Cu
0,08 – 0,18	0,35	0,4-1,0	0,030	0,025	0,70 – 1,15	0,40 – 0,60	0,30

Application area:

Alloyed, for manufacturing boiler and pressure vessels, working temperature to appr. 560°C

Produced in:

Plates 2 - 200 mm
Roundbars Ø 10 – 850 mm
Flatbars (limited dimensions)
Squarebars (limited dimensions)
Pipes/tubes
Forging

For more information, please contact Livalco Stål AB

*The different standards may be the nearest comparable
E & O.E*

LIVALCO STÅL AB • BOX 2, 443 21 Lerum • Visiting adress: Almekärsvägen 11, 443 39 Lerum
Tel.vx: 0302-150 10 • Fax: 0302-120 80 • www.livalco.se • info@livalco.se

SMITH & STENSSON AB • Box 56, 443 21 Lerum • Visiting adress: Almekärsvägen 11, 443 39 Lerum
Tel.vx: 0302-166 60 • Fax: 0302-175 50 • www.livalco.se • info@livalco.se