



LIVALLCO STÅL AB
SMITH & STENSSON

Alloyed **BOILER AND PRESSURE VESSELS STEEL**
acc. to EN 10028, 10273, 10222-2

Euronorm

Sw Std

ASTM

W.St.

Pipes

**16Mo3
(15Mo3)**

SS 2912

A204 gr. A

I.5415

A 335 PI

C	Si	Mn	P	S	Cr	Mo	Ni	N	Cu
0,12-0,20	0,35	0,40-0,90	0,030	0,025	0,30	0,25-0,35	0,30	0,025	0,30

Application area:

Alloyed, for manufacturing boiler and pressure vessels, working temperature to appr. 500°C

Produced in:

Plates
Roundbars
Squarebars
Flatbars
Angles
Pipes/tubes
Forging

1 - 200 mm
Ø 4 – 850mm
4 – 80 mm

For more information, please contact Livalco Stål AB

*The different standards may be the nearest comparable
E & O.E*

LIVALLCO STÅL AB • BOX 2, 443 21 Lerum • Visiting adress: Almekärsvägen 11, 443 39 Lerum
Tel.vx: 0302-150 10 • Fax: 0302-120 80 • www.livalco.se • info@livalco.se

SMITH & STENSSON AB • Box 56, 443 21 Lerum • Visiting adress: Almekärsvägen 11, 443 39 Lerum
Tel.vx: 0302-166 60 • Fax: 0302-175 50 • www.livalco.se • info@livalco.se