



**LIVALLCO STÅL AB**  
**SMITH & STENSSON**

Offshore

API 2H-50 / API 2W-50

**DESIGNATIONS**

Swedish standard  
ASTM / ASME standard  
Similar grade  
W.stoff nr

**CHEMICAL COMPOSITION**

C	max. 0,18
Mn	1,15 - 1,60
Si	0,05 - 0,40

**DIMENSION**

Plate          6 - 200 mm

**MECHANICAL PROPERTIES**

Yield	min. 324 N/mm <sup>2</sup>
Tensile	483 - 620 N/mm <sup>2</sup> Slagseghet